



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 350 907
A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89112799.5

(51) Int. Cl.4: H05B 33/04

(22) Date of filing: 13.07.89

(30) Priority: 14.07.88 JP 175569/88

(43) Date of publication of application:
17.01.90 Bulletin 90/03

(84) Designated Contracting States:
DE FR GB

(71) Applicant: SHARP KABUSHIKI KAISHA
22-22 Nagaike-cho Abeno-ku
Osaka 545(JP)

(72) Inventor: Yamashita, Takuo
99-2, Toyoi-cho
Tenri-shi Nara-ken(JP)
Inventor: Yoshida, Masaru
5-6-1, Tatsutakita Ikaruga-cho Ikoma-gun
Nara-ken(JP)
Inventor: Nakajima, Shigeo
2-7-1-603, Omiya-cho
Nara-shi Nara-ken(JP)
Inventor: Uno, Keiichi
c/o Toyo Boseki K.K. Sogo Kenkyusho 2-1-1,
Katata
Otsu-shi Shiga-ken(JP)
Inventor: Murakami, Yoshiki
c/o Toyo Boseki K.K. Sogo Kenkyusho 2-1-1,
Katata
Otsu-shi Shiga-ken(JP)

(74) Representative: von Kreisler, Alek,
Dipl.-Chem. et al
Patentanwälte Von Kreisler-Selting-Werner
Deichmannhaus am Hauptbahnhof
D-5000 Köln 1(DE)

(54) Thin film electroluminescent panel.

EP 0 350 907 A2

(57) Disclosed is a thin film EL panel having a high reliability. The thin film EL panel is thin, light, and low cost. The present invention provides in a thin film electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption sheet is placed between said thin film EL element, and said moisture-proof sheet and said moisture-absorption sheet comprises an organic polymer sheet and silica gel powder dispersed therein in a certain surface density.
The present invention also provides in a thin film

electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption layer is formed on the inside surface of the moisture proof sheet by coating powder having moisture absorption properties.

THIN FILM ELECTROLUMINESCENT (EL) PANEL

BRIEF EXPLANATION OF THE DRAWINGS

Fig.1 (a) and (b) show enlarged vertical sectional views of the thin film EL panel of the present invention.

Fig.2 shows an enlarged vertical sectional view of the conventional thin film EL panel.

Fig.3 is a graph showing a deterioration degree of the thin film EL panel of the present invention against working time.

FIELD OF THE INVENTION

The present invention relates to a thin film electroluminescent (EL) panel used for a display of a personal computer and a word processor.

BACKGROUND OF THE INVENTION

A conventional thin film EL panel, as shown in Fig.2, is prepared by forming on a glass base plate 2 a lower transparent electrode 3, a lower insulating layer 4, a luminescent layer 5, an upper insulating layer 6 and an upper electrode 7 in this order. The constitution of the layers 3 to 7 is called EL element 1. In order to prevent from reaching moisture to the EL element, the EL element is covered by a glass cover 8 which is adhere to the glass base plate 2 by an epoxy adhesive agent 9. In order to further enhance reliability against moisture, silicone oil containing silica gel powder is encapsulated between the glass cover 8 and the EL element 1 through a hole 17 of the glass cover 8. The hole 17 is sealed by a low vapor pressure resin 'TORR SEAL' (Varian Associate U.S.A.) 11.

However, since the glass cover 8 has to have a certain thickness to ensure protective function, the thin film EL panel is thick and heavy. It is therefore difficult to make the panel thin and light. Also, since the glass cover 8 and the silicone oil are relatively expensive, cost down is difficult. Further, the encapsulating process of the silicone oil takes a long time and complicated.

Japanese Kokai Publication (unexamined) 290693/1986 proposes that a laminate film is used to prevent the EL element from moisture. This element does not pay an attention on absorbing moisture, so that its reliability is low.

SUMMARY OF THE INVENTION

The present invention provides a thin film EL

panel having a high reliability. The thin film EL panel is thin, light, and low cost. The present invention provides in a thin film electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption sheet is placed between said thin film EL element and said moisture-proof sheet, and said moisture-absorption sheet comprises an organic polymer sheet and silica gel dispersed therein in a certain surface density.

The present invention also provides in a thin film EL panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption layer is formed on the inside surface of the moisture-proof sheet by coating powder having moisture absorption properties.

The EL element of the present invention is prepared by forming on a light permeable base plate a lower transparent electrode, a lower insulation layer, an electroluminescent layer, an upper insulation layer and an upper electrode in this order. Either the lower insulation layer or the upper insulation layer can be eliminated.

PREFERRED EXAMPLES OF THE PRESENT INVENTION

Fig.1 (a) and (b) show enlarged vertical sectional views of the thin film EL panel of the present invention. The same elements are shown using the same number.

In Fig.1 (a), 1 shows an EL element which is prepared by forming on a light permeable base plate 1 (e.g. a glass base plate) a lower transparent electrode 3, a lower insulation layer 4, an electroluminescent layer 5, an upper insulation layer 6 and an upper electrode 7 in this order. Either the lower insulation layer 4 or the upper insulation layer 6 can be eliminated.

12 shows a sealing sheet which is composed of a moisture-proof sheet 13 and a moisture-absorption sheet 14. The EL element 1 is covered with the sealing sheet 12 of which the moisture-proof sheet 13 is outside. The sealing sheet 12 covers over the EL element as forming a space 16 and the peripheral portion of the sealing sheet 12 is bonded by an epoxy resin 9 to the permeable base plate 2 on which the lower transparent electrode 3 or the upper transparent electrode 7 may be

present. The moisture-proof sheet 13 may be formed larger than the moisture-absorption sheet 14 so that, as shown in Fig.1, only the peripheral portion of the moisture-proof sheet 13 is used for bonding.

It is preferred that the moisture-proof sheet 13 of the sealing sheet 12, as shown in Fig.1, comprises two organic films 22 (e.g. a polyester film) having a thickness of 5 to 50 micrometer and a metal film 21 (e.g. aluminum) having a thickness of 5 to 50 micrometer sandwiched therebetween. In this preferred construction, moisture-proof properties are brought about by the metal film 21. The organic films 22 act as a protection of the metal film 21 and an insulation of the EL element.

The sealing sheet 12 is generally bonded quickly to the permeable base plate 2 in **dried nitrogen gas**, after heating the element 1 to 200 °C to remove water content from the EL element 1. But, little water content remains by all means. Also, water content would leak in from the bonded portion while the plate works for a long time. Such water content is absorbed into the moisture-absorption sheet 14, according to the present invention.

The moisture-absorption sheet 14 is an organic polymer sheet dispersed with silica gel powder having a particle size of 1-4 micron, preferably 15 micron in a certain surface density, preferably 10 to 500 g/m². The organic polymer sheet can be any polymers, for example natural polymers, such as cellulose, protein and the like; modified natural polymers, such as nitrocellulose, acetylcellulose, cyanoethylcellulose, hydroxyethylcellulose, carboxymethylcellulose and the like; synthetic polymer, such as vinyl polymers (e.g. polyethylene, polypropylene, polyvinylalcohol, polyvinylacetate, polyacrylate, polyvinylchloride, polyvinylidenechloride, polyvinylfluoride, polyvinylidene fluoride), condensation polymers (e.g. polyester, polyamide), thermosetting polymers (e.g. epoxy resin, phenol resin, melamine resin); a mixture thereof; a composite thereof; and the like. The sheet can be any form, such as film, paper, nonwoven fabric, woven fabric and the like. It is in the form of film, preferred is polyvinylalcohol, polyamide, hydroxyethylcellulose, carboxymethylcellulose and the like. In the form of paper, cellulose is preferred. In the form of non-woven fabric, thermoplastic resin (e.g. polyethylene, polypropylene, polyester etc.) is preferred. The moisture-absorption sheet 14 preferably has a thickness of 0.01 to 1 mm. If the sheet 14 is thicker than 1 mm, it obstructs the bond of the sheet 12 to the base plate 2. The moisture-absorption sheet 14 may be either bonded to the moisture-proof sheet 13 or inserted between the EL element 1 and the moisture-proof sheet 13.

If the moisture-absorption sheet 14 of the embodiment of Fig.1 (a) is replaced by the moisture-

absorption layer 15, the second embodiment of the present invention is formed as shown in Fig.1 (b). The moisture-absorption layer 15 can be prepared by coating silica gel powder on the inside surface of the moisture-proof sheet 13. The silica gel powder is preferably dispersed in a surface density amount of 10 to 500 g/m².

In both embodiments of Fig.1 (a) and (b), an amount of silica gel powder is determined by an experiment of Fig.3. The experiment was carried out by changing an amount of silica gel powder and placing the panel at an elevated temperature and a high humidity to determine deterioration degree. The results are expressed as a graph in Fig.3.

In Fig.3, a shows a thin film EL panel without the moisture-absorption sheet or layer, b shows one having a surface density of 0.1 g/m², c is 1 g/m², d is 10 g/m² and e is 500 g/m². A line expressed as f in Fig.3 is a limit over which a quality of a thin film EL panel is bad. As is apparent from Fig.3, surface densities more than 10 g/m² significantly lengthen a life span of the panel. It is very difficult from the technical view points to disperse silica gel powder in a surface density of more than 500 g/m². Technical effects do not increase in proportion to the increase of surface density. Accordingly, a surface density of silica gel powder is defined as within the range of 10 to 500 g/m².

In order to enhance display contrast, it is preferred that the moisture-absorption sheet 14 and layer 15 are colored black or near black.

In the Examples, the EL element of dot-matrix type is explained, but the present invention may also be applied to an element of dot-matrix type.

According to the present invention, since the moisture-absorption sheet or layer is present between the moisture-proof sheet and the EL element, the thin film EL panel has a long life span. The present invention can realize to make light and thin in comparison with conventional techniques.

The present invention has no process for pouring silicone oil and easily produces the thin film EL panel, it makes low cost.

Further, if the moisture-absorption sheet or layer is colored black, it enhances the contrast of display.

Claims

1. In a thin film electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption sheet is placed between said thin film EL element and said

moisture-proof sheet, and said moisture-absorption sheet comprises an organic polymer sheet and silica gel powder dispersed therein in a certain surface density.

2. The thin film EL panel according to Claim 1 wherein said moisture absorption sheet has a thickness of 0.01 to 1 mm and said silica gel powder is dispersed in a surface density of 10 to 500 g/m².

3. In a thin film EL panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption layer is formed on the inside surface of the moisture-proof sheet by coating powder having moisture absorption properties.

4. The thin film EL panel according to Claim 3 wherein said powder is silica and dispersed in a surface density of 10 to 500 g/m².

5. The thin film EL panel according to Claim 1 or Claim 3 wherein said moisture absorption sheet or moisture absorption layer is colored black or near black.

5

10

15

20

25

30

35

40

45

50

55

4

Fig. 1 (a)

Fig. 1 (b)





Fig. 2 PRIOR ART





Fig. 3



(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89112799.5

(51) Int. Cl.⁵: **H 05 B 33/04**

(22) Date of filing: 13.07.89

(30) Priority: 14.07.88 JP 175569/88

(43) Date of publication of application:
17.01.90 Bulletin 90/03

(84) Designated Contracting States: **DE FR GB**

(68) Date of deferred publication of search report:
14.03.90 Bulletin 90/11

(71) Applicant: **SHARP KABUSHIKI KAISHA**
22-22 Nagaike-cho Abeno-ku
Osaka 545 (JP)

(72) Inventor: **Yamashita, Takuo**
99-2, Toyoi-cho
Tenri-shi Nara-ken (JP)

Yoshida, Masaru
5-6-1, Tatsutakita Ikaruga-cho Ikoma-gun
Nara-ken (JP)

Nakajima, Shigeo
2-7-1-603, Omiya-cho
Nara-shi Nara-ken (JP)

Uno, Keiichi
c/o Toyo Boseki K.K. Sogo Kenkyusho 2-1-1, Katata
Otsu-shi Shiga-ken (JP)

Murakami, Yoshiki
c/o Toyo Boseki K.K. Sogo Kenkyusho 2-1-1, Katata
Otsu-shi Shiga-ken (JP)

(74) Representative: **von Kreisler, Alek, Dipl.-Chem. et al**
Patentanwälte Von Kreisler-Selting-Werner
Deichmannhaus am Hauptbahnhof
D-5000 Köln 1 (DE)

(54) **Thin film electroluminescent panel.**

(57) Disclosed is a thin film EL panel having a high reliability. The thin film EL panel is thin, light, and low cost. The present invention provides in a thin film electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption sheet is placed between said thin film EL element, and said moisture-proof sheet and said moisture-absorption sheet comprises an organic polymer sheet and silica gel powder dispersed therein in a certain surface density.

The present invention also provides in a thin film electroluminescent (EL) panel comprising a light permeable base plate, a thin film EL element formed on the base plate and a moisture-proof sheet covered thereon, an improvement residing in that a moisture-absorption layer is formed on the inside surface of the moisture proof sheet by coating powder having moisture absorption properties.

EP 0 350 907 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 11 2799

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	DE-A-3 010 164 (SHARP) * Whole document *	1-5	H 05 B 33/04
X	----- DATABASE DERWENT WORLD PATENT INDEX, no. AN-88-108734(16), Derwent Publications Ltd, London, GB; & JP-A-63 057 230 (DAINIPPON PRINTING K.K.) 11-03-88 * Abstract *	1,3	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			H 05 B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 11-12-1989	Examiner DROUOT M.C.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 01.82 (P0601)